

§ 177.2500

(2) Substances used in accordance with prior sanction or approval.

(3) Substances the use of which is permitted in coatings under regulations in parts 170 through 189 of this chapter.

(c) The finished coatings are thermally cured at temperatures of 700 °F and above.

(d) Polyphenylene sulfide resin coatings may be used in contact with food at temperatures not to exceed the boiling point of water; provided that the finished cured coating, when extracted at reflux temperatures for 8 hours separately with distilled water, 50 percent ethanol in water, and 3 percent acetic acid, yields total extractives in each extracting solvent not to exceed 0.02 milligram per square inch of surface and when extracted at reflux temperature for 8 hours with heptane yields total extractives not to exceed 0.1 milligram per square inch of surface.

(e) Polyphenylene sulfide resin coatings containing perfluorocarbon resins complying with §177.1550 may be used in contact with food at temperatures up to and including normal baking and frying temperatures; provided that the finished cured coating, when extracted at reflux temperatures for 2 hours separately with distilled water, 50 percent ethanol in water, 3 percent acetic acid and heptane, yields total extractives in each extracting solvent not to exceed 0.2 milligram per square inch of surface and when extracted at reflux temperature for 1 hour with diphenyl ether yields total extractives not to exceed 4.5 milligrams per square inch of surface.

[42 FR 14572, Mar. 15, 1977, as amended at 47 FR 11846, Mar. 19, 1982; 54 FR 24898, June 12, 1989]

§ 177.2500 Polyphenylene sulfone resins.

The polyphenylene sulfone resins (CAS Reg. No. 31833-61-1) identified in paragraph (a) of this section may be safely used as articles or components of articles intended for repeated use in contact with food, subject to the provisions of this section.

(a) *Identity.* For the purpose of this section, polyphenylene sulfone resins consist of basic resin produced by reacting polyphenylene sulfide with per-

21 CFR Ch. I (4-1-11 Edition)

acetic acid such that the finished resins meet the specifications set forth in paragraph (c) of this section. The polyphenylene sulfide used to manufacture polyphenylene sulfone is prepared by the reaction of sodium sulfide and *p*-dichlorobenzene, and has a minimum weight average molecular weight of 5,000 Daltons.

(b) *Optional adjuvant substances.* The basic polyphenylene sulfone resins identified in paragraph (a) of this section may contain optional adjuvant substances required in the production of such basic resins. These optional adjuvant substances may include substances permitted for such use by regulations in parts 170 through 189 of this chapter, substances generally recognized as safe in food, or substances used in accordance with a prior sanction or approval.

(c) *Specifications.* The glass transition temperature of the polymer is 360±5 °C as determined by the use of differential scanning calorimetry.

[65 FR 15053, Mar. 21, 2000]

§ 177.2510 Polyvinylidene fluoride resins.

Polyvinylidene fluoride resins may be safely used as articles or components of articles intended for repeated use in contact with food, in accordance with the following prescribed conditions:

(a) For the purpose of this section, the polyvinylidene fluoride resins consist of basic resins produced by the polymerization of vinylidene fluoride.

(b) The finished food-contact article, when extracted at reflux temperatures for 2 hours with the solvents distilled water, 50 percent (by volume) ethyl alcohol in distilled water, and *n*-heptane, yields total extractives in each extracting solvent not to exceed 0.01 milligram per square inch of food-contact surface tested; and if the finished food-contact article is itself the subject of a regulation in parts 174, 175, 176, 177, 178 and §179.45 of this chapter, it shall also comply with any specifications and limitations prescribed for it by that regulation. (NOTE: In testing the finished food-contact article, use a separate test sample for each required extracting solvent.)